



# **ER 307Si**

Stainless Steel WIRE/GTAW



#### **Standards**

**EN/ISO-Standard -** 14343-A **EN/ISO-Classification -** W 18 8 Mn

AWS-Standard - A5.9 AWS-Classification - ER 307Si

#### **Features and Applications**

- Austenitic stainless steel wire with a significant amount of manganese, making the all weld metal in most cases fully austenitic.
- High mechanical strength and excellent crack resistance.
- Increased silicon content promotes weld pool fluidity to give a smooth deposit appearance.
- Ideal for dissimilar welding between steel and stainless steel, armour plate and exhaust systems etc.
- Suitable for depositing stress relaxing buffer layers on crack sensitive base metals including hardfacing.
- Typically used on applications subject to atmospheric and corrosive media's.
- Test Certificates can be found online @wilkinsonstar247.com

#### **Approvals**

CE, UKCA

#### Typical Base Materials

Armour plate, exhaust systems (type 409, 304), high Manganese austenitic steel, difficult to weld steels such as 42CrMo4, C45, 42MnV7, tool steels, 1.3401, X120Mn12 etc.\*

\* Illustrative, not exhaustive list

### **Welding Positions**

EN ISO 6947 - PA, PB, PC, PD, PE, PF

**Shielding Gases** 

**Polarity** 

EN ISO 14175 - TIG: I1 (Argon)

DC (-)

## Mechanical Properties

Tensile Strength	Yield Strength	Elongation	Impact Strength	
(N/mm²)	(N/mm²)	(%)	(J)	
≥500	≥350	≥25		

Mechanical properties are approximate and may vary based on the heat, shielding gas, welding parameters and other factors.

#### Chemical Composition % (Typical)

C %	Mn %	Si %	S %	P %	Ni %	Cr %	Mo %	Cu %
0.045	6.06	0.82	0.005	0.029	8.02	18.35	0.05	0.030

### **Packaging Data**

Part No.	Diameter Ø (mm)	Package Length (mm)	Package Weight (Kg)	Package Type	
6011100113	1.60	1000	5	Plastic Tube	
6011100316	2.40	1000	5	Plastic Tube	
6011100317	3.20	1000	5	Plastic Tube	

Other diameters available on request