

**HARD
CORE**



MAKE THE CHANGE



**ARE YOU TOUGH ENOUGH?
JOIN THE RANKS OF THE HARD CORE WELDING!
CONQUER EVERY SEAM WITH SG2 HARD CORE WIRE**



TECHNICAL DATA SHEET

HARD CORE SG2 (G3Si1)

Mild Steel **WIRE/GMAW**

Standards

EN/ISO-Standard - 14341-A

EN/ISO-Classification - G 42 3 C1 / G 42 4 M21 3Si1

AWS-Standard - A5.18

AWS-Classification - ER 70S-6

Features and Applications

- A copper coated solid wire suitable for single pass or multipass welding of unalloyed and low-alloyed carbon-manganese steels.
- Good mechanical properties at sub-zero temperatures down to -40°C.
- Precision layer wound for superior wire feeding characteristics.
- Typically used on boilers, industrial machinery, bridges, shipbuilding, automotive, rail, structural and engineering fabrications etc.
- Green wire is produced using virgin raw materials sourced from specialised steel mills, which ensures consistent reliability and quality.
- Test Certificates can be found online @wilkinsonstar247.com**



Typical Base Materials

S185, S235, S275, S355 - Grade A, B, D, AH32 to DH36 - L210, L240, L290, L360, L240NB, L290NB, L360NB, L360QB, L240MB, L290MB, L360MB, L415MB - X42, X46, X52, X60 - P235T1, P235T2, P275T1 - P275T2, P355N - P235GH, P265GH, P295GH, P355GH - S275, S355, S420, S275M, S275ML, S355M, S355ML, S420M, S420ML*

* Illustrative, not exhaustive list

Welding Positions

EN ISO 6947 - PA, PB, PC, PD, PE, PF, PG

Shielding Gases

EN ISO 14175 - C1, M21

Polarity

DC (+)

Welding Parameters

Ø mm	0.8	1.00	1.20
Current (A)	60-180	80-300	120-380
Voltage (V)	18-22	18-32	18-34

Mechanical Properties (Typical) - C1

Tensile Strength (N/mm ²)	Yield Strength (N/mm ²)	Elongation (%)	Impact Strength (J)	Test Temperature
540	440	30	70	-30°C

Mechanical Properties (Typical) - M21

Tensile Strength (N/mm ²)	Yield Strength (N/mm ²)	Elongation (%)	Impact Strength (J)	Test Temperature
580	460	26	90	-40°C

Mechanical properties are approximate and may vary based on the heat, shielding gas, welding parameters and other factors.

Chemical Composition % (Typical)

C %	Si %	Mn %	P %	S %	Cu % ^a	Cr %	Ni %	Mo %	Al %	V %	Zr+Ti %
0.07	0.85	1.45	<0.025	<0.025	<0.35	<0.15	<0.15	<0.15	<0.020	<0.030	<0.15

^a (includes copper coating)

Packaging Data

Part No.	Description
HCSG208/15P	HARD CORE SG2 (G3Si1) Wire (0.8mm) 15kg (Plastic)
HCSG210/15P	HARD CORE SG2 (G3Si1) Wire (1.0mm) 15kg (Plastic)
HCSG212/15P	HARD CORE SG2 (G3Si1) Wire (1.2mm) 15kg (Plastic)

Hard Core Approvals



CE acc. EN 10479



TÜV 1153



DB Systemtechnik



UK Conformity Assessed

Liability: Whilst all reasonable efforts have been made to ensure the accuracy of the information contained, this information is subject to change without notice and can be only considered as suitable for general guidance.